

■ Calgary ☎ 403-248-8837 ■ Edmonton ☎ 780-435-2800 ■ London ☎ 519-672-5561 ■ Moncton ☎ 506-384-6101
■ Montreal ☎ 450-655-6676 ■ Ottawa ☎ 613-741-4591 ■ Quebec ☎ 418-681-878801 ■ Saskatoon ☎ 306-651-2647
■ Toronto ☎ 905-760-8211 ■ Vancouver ☎ 604-522-3944 ■ Winnipeg ☎ 204-694-2849

MAMMOUTH SOPRAMASTIC

Description: SOPRAMASTIC is a black, solvent-based mastic containing SBS modified bitumen, fibres and mineral fillers. It is an ideal complement for bituminous waterproofing membranes and is used as jointing mastic, caulking material and joint filler. It is compatible with bituminous materials and ensures good waterproofing.

SOPRAMASTIC is a multi-purpose mastic that has been formulated with a high level of polymer in order to resist flow at high temperatures. Furthermore, it is easy to manipulate at temperatures down to -10°C .

Application: SOPRAMASTIC must be applied to clean, sound substrates.
SOPRAMASTIC tubes can be used with a standard cartridge extruder.
Excellent adherence on most materials without primer. **Can be applied to damp surfaces.**

Properties:

SOPRAMASTIC meets the requirements of CAN/CGSB-37.5-M89 and ASTM D4586 standards.

Properties	SOPRAMASTIC
Specific gravity at 20°C (kg/l)	1.12
Colour	Black
Application Temperature Range (°C)	-10 to 35 (14 to 95 °F)
Service Temperature Range (°C)	-40 to 80 (-40 to 175 °F)
Solids by Weight (%)	83
Flash point (ASTM D-93)	25°C (77°F)
Setting time	Between 4 and 24 hours depending on temperature and quantity applied.

(All values are nominal)

Packaging: 310 ml (20 per boxes) & 800 ml cartridges, and 10 L pails.
Shelf life: Up to 12 months in original sealed containers.

Cleaning: Tools can be cleaned with petroleum solvents such as mineral spirits, varsol, xylene, etc.

Precautions: SOPRAMASTIC is a flammable product. Store in a cool, dry area.
CONSULT THE MATERIAL SAFETY DATA SHEET PRIOR TO USE.



NOTE: SOPREMA INC. may modify the composition and/or utilisation of its products without prior notice. Consequently orders will be filled according to the latest specification.